



01/2009

:: UNIFLEX MS

sprayable seam sealer

CHARACTERISTICS

Permanently elastic, sprayable, single-component seam sealer. Uniflex MS is a polyoxypropylene-mixed-polymer-based product that cures on exposure to atmospheric moisture. Uniflex MS adheres well to glass, many metals (zinc, aluminum, steel), paint and primer, wood, thermosets and thermoplastics (except PE, PP, and PTFE). This product is highly resistant to moisture, weathering, and extreme temperatures.

APPLICATION

For use in vehicle/body repair, container construction, HVAC technology, metal construction, etc.

PRODUCT DATA

Packaging: 310 mL container

Color: Gray

Density: 1.48 kg/L

Application temperature: 5 – 30°C

Skin formation time: 35 min.

Hardening(DIN 50 014): Approx. 3 mm after 24 hours

Elongation at tear(DIN 53 504): 330 %

Tensile strength(DIN 53 504): 0.8 N/mm

Heat and cold resistance: -40°C to +80°C

Resistance to tear propagation (DIN 53 515): 5.0 N/mm

HANDLING

The substrate must be clean, dry, and free of dust, grease and oil. Test Uniflex MS



01/2009

on a case-by-case basis to check adhesion and compatibility. Use the MS Pneumatic Spray Gun to apply the product to structural and profile seams as well as surface coatings. Immediately after applying Uniflex MS, you can paint over it with most paints (for up to two hours). If you wait longer to apply paint, some paints may not adhere as well.

PRECAUTIONS

Do not bring Uniflex MS into contact with new polyurethane material that has not hardened completely.

There must always be a cartridge in the spray gun. Never put the spray gun away empty. The material in the spray gun will dry out if you do this.

Clean the spray gun and all other tools immediately after use. Dried-on material can only be removed mechanically.

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Security Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE