



:: Uniflex PU

bonding and sealing compound

CHARACTERISTICS

UNIFLEX-PU adhesive and sealant is an elastic one component polyurethane that is air cured. UNIFLEX-PU has powerful adhesion to most surfaces. The treated surface can be sanded and overpainted with acrylic or 2 component paints. For synthetic resin based paints we recommend to carry out a test. The material is highly resistant to water (also seawater), low concentrations of acids and alkalis and for a limited time to fuel and mineral oils. The colours white and grey may yellow when exposed to UV light.

APPLICATION

UNIFLEX-PU is used for filling and sealing seams and joints and protecting welding seams against corrosion. It provides an elastic joint to metal (bare, primed or painted), G.R.P., wood, brick and concrete. UNIFLEX-PU is not suitable for use on woods containing oil (e.g. teak).

PRODUCT DATA

Colours: White / black / grey
Specific gravity: ca. 1,2 kg/l
Formation of skin: ca. 45 minutes
Curing rate: ca. 3 mm (first day)
Linear shrinkage: ca. 6 %
Elongation at tear: ca. 450 %
Tensile strength: ca. 2 N/mm²
Shearing strength: ca. 1,5 N/mm²
Tear propagation: ca. 9 N/mm
Shore hardness A: ca. 45
Temperature Resistance -40°C up to +90°C



01/2009

Shelf life: Min. 9 months in closed original container at max. 25°C

HANDLING

The surface must be dry, clean, oil and grease free. The surface temperature should be between 10 and 25°C. Carry out a test to establish its compatibility and adhesion to plastics and paints. UNIFLEX-PU is not overpaintable with hydrous acrylate systems.

Important: Absorbent surfaces must be primed with UNIFLEX PRIMER-S.

Remove the aluminium base plate with a screw driver and discard the lid. Pierce the membrane in the top of the cartridge and screw on the nozzle. Cut the plastic nozzle so as to provide the required diameter and formate for the extrusion or bead. Close the cartridge hermetically, the shelf life is very limited.

The UNIFLEX-PU bead can be shaped or spread after a short hardening time without tearing. Use a finger, but wear a wetted glove or use a wetted applicator when filling joints.

Bonding: Apply the material with a spreader or directly from the cartridge to the surface. The application amount depends on the nature of the materials to be bonded. Insert the counter part within 10 minutes and press the parts together. Due to the consistency of UNIFLEX-PU it is recommended to fix the repair until it is cured.

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed.



01/2009

Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Security Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE